



**UNIVERSITI PUTRA MALAYSIA**

**WOOD QUALITY OF XYLIA XYLOCARPA AND KHAYA IVORENSIS  
PLANTED IN SABAH**

**JAMES JOSUE**

**FH 2002 11**

**WOOD QUALITY OF *XYLIA XYLOCARPA* AND *KHAYA IVORENSIS*  
PLANTED IN SABAH**

**By**

**JAMES JOSUE**

**Thesis Submitted to the School of Graduate Studies, Universiti Putra  
Malaysia, in Fulfilment of the Requirements for the Degree of Master of  
Science**

**April 2002**



*To:  
my beloved wife Flosie  
&  
sons (Neville & Lovink)*

Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfilment of the requirements for the degree of Master of Science

**WOOD QUALITY OF *XYLIA XYLOCARPA* AND *KHAYA IVORENSIS*  
PLANTED IN SABAH**

By

**JAMES JOSUE**

**April 2002**

**Chairman: Associate Professor Mohd. Hamami Sahri, Ph.D.**

**Faculty: Forestry**

*Xylia xylocarpa* and *Khaya ivorensis* are two fast-growing trees that are currently planted on trial basis in Sabah. The wood quality of trees grown in Sabah may differ from those grown in other places due to the environmental factors. Five 9-year-old trees of each species were extracted from their respective plots at Luasong, Tawau. Wood specimens were prepared from three height levels; bottom, middle and top, at the inner and outer radial positions. The within-tree and between-tree variations of anatomical, physical and mechanical properties of these species were analysed.

The characteristics of *X. xylocarpa* are comparable to a number of local popular hardwood species, indicating its suitability for heavy construction uses. The mean vessel diameter, ray width, ray height and fibre length are 124  $\mu\text{m}$ , 49.8  $\mu\text{m}$ , 605  $\mu\text{m}$  and 1135  $\mu\text{m}$ , respectively. The basic density, oven-dry density and green moisture content (MC) are 0.72  $\text{g}/\text{cm}^3$ , 0.78  $\text{g}/\text{cm}^3$  and 49.8% respectively. The shrinkage from green to oven-dry conditions

for the radial and tangential directions are 3.35% and 5.76%, respectively. Based on the International Standard Organisation (ISO) standard, the overall means for modulus of rupture (MOR), modulus of elasticity (MOE), compression parallel to grain (Comp), radial shear (Shear-R), tangential shear (Shear-T), radial hardness (Hard-R) and tangential hardness (Hard-T) are 135 N/mm<sup>2</sup>, 12861 N/mm<sup>2</sup>, 68.3 N/mm<sup>2</sup>, 18.95 N/mm<sup>2</sup>, 23.38 N/mm<sup>2</sup>, 7.86 kN and 7.40 kN, respectively.

The wood properties of *K. ivorensis* are comparable to a number of fast-growing light hardwood species, indicating its potential for general utility timber. The vessel diameter, ray width, ray height and fibre length are 118 µm, 56.6 µm, 306 µm and 1351 µm, respectively. The mean basic density, oven-dry density and green MC are 0.44 g/cm<sup>3</sup>, 0.48 g/cm<sup>3</sup> and 55.4%, respectively. The shrinkage from green to oven-dry conditions for the radial and tangential directions are 3.20% and 7.26%, respectively. The overall means for MOR, MOE, Comp, Shear-R, Shear-T, Hard-R and Hard-T are 71.11 N/mm<sup>2</sup>, 6873 N/mm<sup>2</sup>, 38.21 N/mm<sup>2</sup>, 9.48 N/mm<sup>2</sup>, 13.49 N/mm<sup>2</sup>, 2.64 kN and 2.72 kN, respectively.

The trend of within-tree variations for most properties were more consistent in radial rather than vertical direction. This suggests diameter growth to be a more important factor contributing to the variations compared to height. Samples from the outer part of the stem were found to have higher density, shrinkage and mechanical strengths. The between-trees variations of some wood properties were found to be significantly different, probably due to genetic and micro-environmental factors.

Significant correlation was recorded among the physical properties of both species. The regression analysis indicated that the density of *X. xylocarpa* could be best predicted based on fibre length and vessel diameter ( $R^2 = 0.56$ ), and the best single predictor is fibre length ( $R^2 = 0.51$ ). The vessel diameter was found to be the main predictor for the density of *K. ivorensis*. The density was also the best predictor for all mechanical properties, irrespective of the tree species.

The true potential of *X. xylocarpa* and *K. ivorensis* for their respective end-uses would be enhanced by further research such as the study on properties of wood from different sites and other properties like durability, seasoning, processing and machining characteristics.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia  
sebagai memenuhi keperluan untuk ijazah Master Sains

**KUALITI KAYU *XYLIA XYLOCARPA* DAN *KHAYA IVORENSIS* YANG  
DITANAM DI SABAH**

Oleh

**JAMES JOSUE**

**April 2002**

**Pengerusi: Profesor Madya Mohd. Hamami Sahri, Ph.D.**

**Fakulti: Perhutanan**

*Xylia xylocarpa* dan *Khaya ivorensis* merupakan pokok cepat tumbuh yang sedang ditanam secara percubaan di Sabah. Kualiti kayu bagi pokok-pokok yang ditanam di Sabah mungkin berbeza dengan pokok-pokok yang ditanam di tempat yang lain oleh sebab faktor alam sekitar. Lima pokok yang berusia sembilan tahun dari setiap spesis telah diperolehi dari plot masing-masing di Luasong, Tawau. Sampel diambil daripada tiga paras ketinggian iaitu, bawah, tengah dan atas dan daripada dua kedudukan jejari iaitu, bahagian dalaman dan luaran untuk mendapatkan spesimen bagi kajian variasi ciri-ciri anatomi, fizikal dan mekanikal di dalam dan di antara pokok-pokok.

*X. xylocarpa* mempunyai ciri-ciri kayu yang setanding dengan beberapa spesis kayu keras berat tempatan yang terkenal, menggambarkan kesesuaiannya untuk digunakan dalam industri binaan. Purata garispusat vesel, lebar ruji, ketinggian ruji dan panjang gentian masing-masing ialah 124  $\mu\text{m}$ , 49.8  $\mu\text{m}$ , 605  $\mu\text{m}$  dan 1135  $\mu\text{m}$ . Ketumpatan asas, ketumpatan kering

ketuhar dan kandungan lembapan segar masing-masing adalah  $0.72 \text{ g/cm}^3$ ,  $0.78 \text{ g/cm}^3$  dan 49.82%. Kadar pengecutan dari keadaan segar hingga kering ketuhar pada arah jejari dan tangen masing-masing ialah 3.35% dan 5.76%. Berdasarkan piawaian International Standard Organisation (ISO), purata modulus kepecahan (MOR), modulus kekenyalan (MOE), mampatan selari dengan ira (Comp), kekuatan ricih radial (Shear-R), kekuatan ricih tangen (Shear-T), nilai kekerasan radial (Hard-R) dan nilai kekerasan tangen (Hard-T) masing-masing adalah  $135 \text{ N/mm}^2$ ,  $12861 \text{ N/mm}^2$ ,  $68.30 \text{ N/mm}^2$ ,  $18.95 \text{ N/mm}^2$ ,  $23.38 \text{ N/mm}^2$ , 7.86 kN dan 7.40 kN.

*K. ivorensis* mempunyai ciri-ciri kayu yang setanding dengan beberapa spesis kayu keras ringan jenis cepat tumbuh, menggambarkan kesesuaiannya untuk pelbagai kegunaan am. Purata garispusat vesel, lebar ruji, ketinggian ruji dan panjang gentian masing-masing ialah  $118 \mu\text{m}$ ,  $56.6 \mu\text{m}$ ,  $306 \mu\text{m}$  dan  $1351 \mu\text{m}$ . Ketumpatan asas, ketumpatan kering ketuhar dan kandungan lembapan segar masing-masing adalah  $0.45 \text{ g/cm}^3$ ,  $0.48 \text{ g/cm}^3$  dan 55.45%. Kadar pengecutan dari keadaan segar hingga kering ketuhar pada arah jejari dan tangen masing-masing ialah 3.20% dan 7.26%. Purata MOR, MOE, Comp, Shear-R, Shear-T, Hard-R dan Hard-T masing-masing adalah  $71.11 \text{ N/mm}^2$ ,  $6873 \text{ N/mm}^2$ ,  $38.21 \text{ N/mm}^2$ ,  $9.48 \text{ N/mm}^2$ ,  $13.49 \text{ N/mm}^2$ , 2.64 kN dan 2.72 kN.

Variasi di dalam pokok bagi kebanyakan ciri-ciri kayu adalah lebih konsisten pada arah jejari atau mendatar berbanding dengan arah menegak. Ini menggambarkan pertumbuhan diameter pokok adalah faktor yang lebih penting kepada variasi, berbanding ketinggian. Sampel daripada bahagian luaran didapati mempunyai ketumpatan, kadar pengecutan dan



kekuatan mekanikal yang lebih tinggi. Variasi di antara pokok-pokok bagi beberapa ciri-ciri kayu didapati mempunyai perbezaan yang bererti, mungkin disebabkan faktor genetik dan alam sekitar.

Perkaitan yang bererti telah diperolehi di antara ciri-ciri fizikal kedua-dua spesies. Analisa regresi menunjukkan bahawa ketumpatan *X. xylocarpa* boleh diramal dengan baik oleh faktor panjang gentian dan garispusat vesel ( $R^2 = 0.56$ ), dan panjang gentian ( $R^2 = 0.51$ ) merupakan faktor tunggal yang terbaik untuk meramal nilai ketumpatan. Garispusat vesel didapati sebagai peramal utama ketumpatan *K. ivorensis*. Ketumpatan juga menjadi peramal terbaik untuk semua ciri-ciri mekanikal kedua-dua spesies.

Potensi kegunaan-akhir sebenar *X. xylocarpa* dan *K. ivorensis* akan menjadi lebih jelas melalui penyelidikan susulan seperti kajian ke atas ciri-ciri kayu dari tempat yang berbeza, dan kajian ciri-ciri yang lain seperti ketahanan semulajadi, pengeringan, pemprosesan dan pemesinan.

## ACKNOWLEDGEMENTS

The author wishes to express his deepest appreciation to his major Supervisor, Associate Prof. Dr. Hj. Mohd. Hamami Bin Hj. Sahri for his guidance as well as constructive criticisms and suggestions throughout the study period. The project's supervisory committee is also greatly acknowledged.

Great appreciation is extended to the Head of Management of Rakyat Berjaya Sdn. Bhd. Yayasan Sabah and Senior Forest Officers at Luasong Forestry Centre, Tawau, particularly Mr. David Alloysius, for their interest and cooperation in the project and making available the wood materials for the research.

Special acknowledgement is due to the Director of Forestry Department, Sabah, Mr. Daniel Khiong and the Head of Forest Research Centre (FRC), Sandakan, Sabah, Dr. Sining Unchi for their support and encouragement throughout the study. The author is also greatly indebted to his friends at the Forest Products Branch, FRC (Zamrie, Misalam, Ignatius, Clement, Jerry, Kennedy, Rusli, Daud, Albert, Juvilis and others) for their help in carrying out the actual preparation of samples and experiments.

Last but not least, the author wishes to express his most sincere appreciation to his wife, for her love, encouragement and total devotion throughout the entire study period to make this study successful.

I certify that an Examination Committee met on 12<sup>th</sup> April 2002 to conduct the final examination of James Josue on his Master of Science thesis entitled “Wood Quality of *Xylia xylocarpa* and *Khaya ivorensis* Planted in Sabah” in accordance with Universiti Pertanian Malaysia (Higher Degree) Act 1980 and Universiti Pertanian Malaysia (Higher Degree) Regulations 1981. The Committee recommends that the candidate be awarded the relevant degree. Members of the Examination Committee are as follows:

**MOHD. ZIN JUSOH**

Professor,  
Faculty of Forestry  
Universiti Putra Malaysia  
(Chairman)

**MOHD. HAMAMI SAHRI, Ph.D.**

Associate Professor,  
Faculty of Forestry  
Universiti Putra Malaysia  
(Member)

**ZAIDON ASHAARI, Ph.D.**

Associate Professor,  
Faculty of Forestry  
Universiti Putra Malaysia  
(Member)

**WONG EE DING, Ph.D.**

Faculty of Forestry  
Universiti Putra Malaysia  
(Member)

**SINING UNCHI, Ph.D.**

Forest Research Centre,  
Sandakan, Sabah  
(Member)



**SHAMSHER MOHAMMAD RAMADILI, Ph.D.**

Professor/Deputy Dean  
School of Graduate Studies  
Universiti Putra Malaysia

Date: 06 MAY 2002

The thesis submitted to the Senate of Universiti Putra Malaysia has been accepted as fulfilment of the requirement for the degree of Master Science.



---

**AINI IDERIS, Ph.D.**

Professor/Dean

School of Graduate Studies

Universiti Putra Malaysia

Date: **13** JUN 2002

## DECLARATION

I hereby declare that the thesis is based on my original work except for quotations and citations which have been duly acknowledged. I also declare that it has not been previously or concurrently submitted for any other degree at UPM or other institutions.



---

**James Josue**

Date: 3/5/2002

## TABLE OF CONTENTS

	<b>Page</b>
DEDICATION .....	ii
ABSTRACT.....	iii
ABSTRAK.....	vi
ACKNOWLEDGEMENTS.....	ix
APPROVAL SHEETS.....	x
DECLARATION.....	xii
TABLE OF CONTENTS.....	xiii
LIST OF TABLES.....	xvii
LIST OF FIGURES.....	xix
LIST OF PLATES.....	xxi
LIST OF ABBREVIATIONS.....	xxii

## CHAPTER

<b>I</b>	<b>INTRODUCTION.....</b>	<b>1</b>
	Introduction.....	1
	Justification.....	5
	Objectives.....	6
<b>II</b>	<b>LITERATURE REVIEW.....</b>	<b>7</b>
	General Characteristics of <i>Xylia xylocarpa</i> .....	7
	Growth and Yield of <i>Xylia xylocarpa</i> .....	12
	Wood Properties and Uses of <i>Xylia xylocarpa</i> .....	13
	General Characteristics of <i>Khaya ivorensis</i> .....	14
	Growth and Yield of <i>Khaya ivorensis</i> .....	19
	Wood Properties and Uses of <i>Khaya ivorensis</i> .....	19
	Wood Anatomical Features.....	20
	Vessel.....	20
	Fibre.....	21
	Ray.....	22
	Wood Physical Properties.....	23
	Density.....	23
	Moisture Content.....	25
	Shrinkage.....	26
	Wood Mechanical Properties.....	28
	Static Bending.....	29
	Compression Parallel to Grain.....	30
	Shear Parallel to Grain.....	31
	Hardness .....	31
	Factors Affecting Wood Properties.....	32
	Relationship of Wood properties.....	33



<b>III</b>	<b>MATERIALS AND METHODS.....</b>	<b>35</b>
	Field Sampling.....	35
	Sample Preparation.....	37
	Analysis of Data.....	39
<b>IV</b>	<b>ANATOMICAL PROPERTIES OF PLANTED XYLIA XYLOCARPA AND KHAYA IVORENSIS.....</b>	<b>40</b>
	Introduction.....	40
	Materials and Methods.....	41
	Softening and Sectioning of Wood Blocks.....	41
	Dehydration, Staining and Mounting Process.....	42
	Vessel and Ray Measurement.....	44
	Fibre Length Determination.....	45
	Results and Discussion.....	47
	Anatomical Properties of <i>Xylia xylocarpa</i> .....	47
	Variations in Anatomical Properties of <i>Xylia xylocarpa</i> .....	51
	Within-Tree.....	51
	Between-Trees.....	52
	Anatomical Properties of <i>Khaya ivorensis</i> .....	53
	Variations in Anatomical Properties of <i>Khaya ivorensis</i> .....	57
	Within-Tree.....	57
	Between-Trees.....	58
	Conclusion.....	58
<b>V</b>	<b>PHYSICAL PROPERTIES OF PLANTED XYLIA XYLOCARPA AND KHAYA IVORENSIS.....</b>	<b>60</b>
	Introduction.....	60
	Material and Methods.....	61
	Sample Preparation.....	61
	Green Moisture Content.....	63
	Density of Green Wood.....	64
	Density of Oven-dry Wood.....	64
	Shrinkage Determination.....	65
	Results and Discussion.....	66
	Physical Properties of <i>Xylia xylocarpa</i> .....	66
	Variations in Physical Properties of <i>Xylia xylocarpa</i> .....	68
	Physical Properties of <i>Khaya ivorensis</i> .....	74
	Variations in Physical Properties of <i>Khaya ivorensis</i> .....	76
	Conclusion.....	80
<b>VI</b>	<b>MECHANICAL PROPERTIES OF PLANTED XYLIA XYLOCARPA AND KHAYA IVORENSIS.....</b>	<b>82</b>
	Introduction.....	82
	Materials and Methods.....	83

Preparation of Sample.....	83
Evaluation of Mechanical Properties.....	83
Static Bending.....	85
Compression Parallel to Grain.....	87
Shear Parallel to Grain.....	88
Hardness .....	89
Results and Discussion.....	91
Mechanical Properties of <i>Xylia xylocarpa</i> .....	91
Variations in Mechanical Properties of <i>Xylia xylocarpa</i> .....	92
Mechanical Properties of <i>Khaya ivorensis</i> .....	98
Variations in Mechanical Properties of <i>Khaya ivorensis</i> .....	100
Conclusion.....	104
 <b>VII      RELATIONSHIPS AMONG WOOD PROPERTIES OF</b>	
<b>    XYLIA XYLOCARPA AND KHAYA IVORENSIS.....</b>	<b>105</b>
Introduction.....	105
Materials and Methods.....	106
Correlation Analysis.....	106
Regression Analysis.....	107
Results and Discussion.....	107
Relationship Among Wood Properties of <i>Xylia xylocarpa</i> .....	107
Correlation Among Anatomical Properties.....	107
Correlation Among Physical Properties.....	108
Relationship Between Density and Anatomical Properties.....	110
Relationship Between Density and Mechanical Properties.....	111
Relationship Among Wood Properties of <i>Khaya ivorensis</i> .....	112
Correlation Among Anatomical Properties.....	112
Correlation Among Physical Properties.....	113
Relationship Between Density and Anatomical Properties.....	114
Relationship Between Density and Mechanical Properties.....	115
Conclusion.....	116
 <b>VIII    GENERAL CONCLUSION AND RECOMMENDATIONS.....</b>	<b>117</b>
 <b>REFERENCES.....</b>	<b>120</b>



<b>APPENDIX A</b>	<b>Analysis of Variance of Anatomical, Physical and Mechanical Properties of Planted 9-year-old <i>Xylia xylocarpa</i> and <i>Khaya ivorensis</i>.....</b>	<b>130</b>
A <sub>1</sub>	Table 27: Vertical Variations of Anatomical Properties of <i>X. xylocarpa</i> ...	131
A <sub>1</sub>	Table 28: Vertical Variations of Physical Properties of <i>X. xylocarpa</i> .....	131
A <sub>2</sub>	Table 29: Vertical Variations of Physical Properties of <i>K. ivorensis</i> .....	132
A <sub>2</sub>	Table 30: Vertical Variations of Mechanical Properties of <i>X. xylocarpa</i> ...	132
A <sub>3</sub>	Table 31: Vertical variations of Mechanical Properties of <i>K. ivorensis</i> ...	133
<b>VITA</b>	.....	<b>134</b>

## LIST OF TABLES

Table		Page
1	MAI of Plantation Species in Malaysia	13
2	Sample Trees of <i>X. xylocarpa</i> and <i>K. ivorensis</i>	37
3	Wood Anatomical Properties of <i>X. xylocarpa</i>	48
4	Analysis of Variance of Anatomical Properties of <i>X. xylocarpa</i>	51
5	Wood Anatomical Properties of <i>K. ivorensis</i>	55
6	Analysis of Variance of Anatomical Properties of <i>K. ivorensis</i>	57
7	Physical Properties of 9-year-old <i>X. xylocarpa</i>	66
8	Wood Basic Density of Plantation Species	67
9	Summary of ANOVA on the Physical Properties of <i>X. xylocarpa</i>	69
10	Physical Properties of 9-year-old <i>K. ivorensis</i>	75
11	Summary of ANOVA on the Physical Properties of <i>K. ivorensis</i>	76
12	Wood Samples for Mechanical Properties Evaluation	85
13	Mechanical Properties of 9-year-old <i>X. xylocarpa</i>	91
14	Mechanical Properties of Some Heavy Hardwood Species	92
15	Analysis of Variance of Mechanical Properties of <i>X. xylocarpa</i>	93
16	Mechanical Properties of 9-year-old <i>K. ivorensis</i>	99
17	Mechanical Properties Some Medium Hardwood Species	100
18	Analysis of Variance in Mechanical Properties of <i>K. ivorensis</i>	101
19	Correlation Analysis in Anatomical Properties of <i>X. xylocarpa</i>	108
20	Correlation Analysis in Physical Properties of <i>X. xylocarpa</i>	109
21	Relationship among Density and Anatomical Properties of <i>X.</i>	

	<i>xylocarpa</i>	110
22	Relationship among Density and Mechanical Properties of <i>X. xylocarpa</i>	111
23	Correlation Analysis in Anatomical Properties of <i>K. ivorensis</i>	112
24	Correlation Analysis in Physical Properties of <i>K. ivorensis</i>	113
25	Relationship among Density and Anatomical Properties of <i>K. ivorensis</i>	114
26	Relationship among Density and Mechanical Properties of <i>K. ivorensi</i>	115
27	Vertical Variations of Anatomical Properties of <i>X. xylocarpa</i>	131
28	Vertical Variations of Physical Properties of <i>X. xylocarpa</i>	131
29	Vertical Variations of Physical Properties of <i>K. ivorensis</i>	132
30	Vertical Variations of Mechanical Properties of <i>X. xylocarpa</i>	132
31	Vertical Variations of Mechanical Properties of <i>K. ivorensis</i>	133

## LIST OF FIGURES

Figure		Page
1	Location of Lusong Forestry Centre, Tawau, Sabah	36
2	Sampling Points within a Selected Tree	38
3	Flow Chart of Staining and Dehydration Process	43
4	Arrangement of Thin Wood Sections on Glass Slide	44
5	Preparation of Samples for Physical Properties Determination	62
6	Moisture Content at Different Radial Positions in <i>X. xylocarpa</i>	70
7	Basic Density at Various Height Levels in <i>X. xylocarpa</i>	71
8	Basic Density at Different Radial Positions in <i>X. xylocarpa</i>	72
9	Shrinkage of Wood of <i>X. xylocarpa</i> (Green to Air-dry)	73
10	Moisture Content at Different Radial Positions in <i>K. ivorensis</i>	77
11	Basic Density at Various Height Levels in <i>K. ivorensis</i>	78
12	Basic Density at Different Radial Positions in <i>K. ivorensis</i>	78
13	Shrinkage of Wood of <i>K. ivorensis</i> (Green to Oven-dry)	79
14	The Preparation of Sample for Mechanical Properties Evaluation	84
15	Compression at Various Height Levels of <i>X. xylocarpa</i>	93
16	Shear Strength at Various Height Levels of <i>X. xylocarpa</i>	94
17	Hardness at Various Height Levels of <i>X. xylocarpa</i>	94
18	MOR at Different Radial Positions in <i>X. xylocarpa</i>	96
19	MOE at Different Radial Positions in <i>X. xylocarpa</i>	96

20	Shear Strength at Different Radial Positions in <i>X. xylocarpa</i>	97
21	Compression at Different Radial Position in <i>X. xylocarpa</i>	97
22	Hardness at Different Radial Positions in <i>X. xylocarpa</i>	98
23	Hardness at Various Height Levels of <i>K. ivorensis</i>	101
24	MOR at Different Radial Positions in <i>K. ivorensis</i>	102
25	Compression at Different Radial Positions in <i>K. ivorensis</i>	103
26	Hardness at Different Radial Positions in <i>K. ivorensis</i>	103

## LIST OF PLATES

Plate		Page
1	Nine-year- old Stand of <i>X. xylocarpa</i> in Luasong, Tawau	9
2	Sprouting Coppices of <i>X. xylocarpa</i>	10
3	Bark of the Stem of <i>X. xylocarpa</i>	11
4	Nine-year- old stand of <i>K. ivorensis</i> in Luaong, Tawau	16
5	Sprouting Coppices of <i>K. ivorensis</i>	17
6	Bark of the Stem of <i>K. ivorensis</i>	18
7	Nikon V 12 Profile Projector	45
8	Matchstick-Sized Wood for Maceration Process	46
9	Transverse Disc of <i>X. xylocarpa</i>	47
10	Cross-section of <i>X. xylocarpa</i> Showing Vessel Arrangement Pattern	49
11	Tangential -section of <i>X. xylocarpa</i>	50
12	Transverse Disc of <i>K. ivorensis</i> Stem	53
13	Cross-section of <i>K. ivorensis</i> Showing Vessel Arrangement Pattern	54
14	Tangential-section of <i>K. ivorensis</i>	56
15	Static Bending Test	86
16	Compression Parallel to Grain Test	87
17	Shear Test	89
18	Hardness Test	90

## LIST OF ABBREVIATIONS

ANOVA	Analysis of Variance
Comp.	Compression Parallel to Grain
DBH	Diameter Breast Height
EMC	Equilibrium Moisture Content
FL	Fibre Length
FRC	Forest Research Centre
FRIM	Forest Research Institute Malaysia
FSP	Fibre Saturation Point
Hard-R	Radial Hardness
Hard-T	Tangential Hardness
ISO	International Standard Organisation
LFC	Luasong Forestry Centre
MAI	Mean Annual Increment
MC	Moisture Content
MOR	Modulus of Rupture
MOE	Modulus of Elasticity
R-W	Ray Width
R-H	Ray Height
SAFODA	Sabah Forestry Development Authority
SD	Standard Deviation
SFI	Sabah Forest Industries Sdn Bhd.
Shear-R	Radial Shear
Shear-T	Tangential Shear
TAPPI	Technical Association of Pulp and Paper
V	Vessel Diameter

## CHAPTER I

### INTRODUCTION

Sabah is one of the 13 states in Malaysia. It extends between latitudes of 4° 7' and 7° 23' north of the equator and between longitudes of 115° 7' and 119° 17' east of Greenwich, covering an area of 7, 394,191 hectares or approximately 22 percent of the total area of Malaysia. The forestry sector has always been the backbone of Sabah's economy. During the period of 1980-1997, forestry contributed an average of about RM2.69 billion per year in terms of foreign exchange earnings through the export of forest products, while revenue from forest resources was at an average of RM717.5 million annually (Anon., 1997). However, past exploitation of the forest resource has reduced the production capacity of the natural forest. Major commercial timber resources are dwindling and the timber processing industry is desperately searching for additional and alternative raw materials.

In light of this, forest plantation or man-made forest has been gaining importance, not only for the supply of raw materials, but also to sustain the existing timber resources. The state policy on forest plantations emphasises on long term strategy to switch the production base from natural forest to plantation forest which shall provide the bulk of the production capacity. The long term target is to produce at least 6 million m<sup>3</sup> of planted woods annually without compromising the tendency to substitute natural forest with plantation forests (Anon., 1997). Accordingly, there has been a dramatic increase in the area of plantation forests in Sabah. At the end of 1999, plantation forest for timber supply covered approximately 138,400 hectares of



the total planted area which include 23,600 hectares of rattan, established mainly by the private sectors (Anuar, 1997).

The importance of forest plantations in the state is also reflected by the establishment of a number of new agencies which are involved in the research and development of forest plantation. Initially, most of the development of commercial forest plantation were carried out by Sabah Softwood Sdn. Bhd. (SSSB), Sabah Forestry Development Authority (SAFODA) and Sabah Forest Industries Sdn. Bhd. (SFI). However, the late 1980's and early 1990's witnessed the participation of other privately owned companies and individuals such as Luasong Forestry Centre (LFC), Sejati Sdn. Bhd., Koprosa Sdn. Bhd., Boonrich Sdn. Bhd and KTS (Plantation) Sdn. Bhd..

The preferred species for planting are mostly exotic species like *Acacia mangium*, *Paraserianthes falcataria*, *Gmelina arborea*, *Eucalyptus* spp., *Araucaria* spp. and *Pinus* spp. mainly due to their fast growing characteristic and their ability to produce quality timber or at least timber for general purposes. Of late, many new private companies have shown keen interest to venture into plantations of *Tectona grandis* (teak) and *Azadiractha excelsa* (sentang) which are being intensively promoted in Malaysia.

Obviously, the existence of many promising fast-growing exotic species has or may have provided the wood-based industry with new resources of raw material. However, technical issues relating to species choice and utilisation potential need further research and development work. The ever increasing demand of forest produces globally would need to